

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 August 2001 (16.08.2001)

PCT

(10) International Publication Number
WO 01/59270 A1

(51) International Patent Classification⁷: F01N 3/01, 3/08

(21) International Application Number: PCT/GB01/00442

(22) International Filing Date: 2 February 2001 (02.02.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

PCT/GB00/00397

10 February 2000 (10.02.2000) GB

PCT/GB00/00714

28 February 2000 (28.02.2000) GB

0015952.5

30 June 2000 (30.06.2000) GB

(71) Applicant (for all designated States except US): ACCENTUS PLC [GB/GB]; 329 Harwell, Didcot, Oxfordshire OX11 0QJ (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): SEGAL, David, Leslie [GB/GB]; 43 Foxborough Road, Radley, Abingdon, Oxfordshire OX14 3AB (GB). RAYBONE, David [GB/GB]; 1 Talbot Cottages, Fosse Way, Stow-on-the-Wold, Gloucestershire GL54 1DW (GB). SHAWCROSS, James, Timothy [GB/GB]; 27 Ticknell

Piece Road, Charlbury, Oxfordshire OX7 3TN (GB). INMAN, Michael [GB/GB]; 2 Longfellow Drive, Abingdon, Oxfordshire OX14 5NU (GB).

(74) Agents: LOFTING, Marcus, John et al.; Accentus plc, Patents Dept. 329 Harwell, Didcot, Oxfordshire OX11 0QJ (GB).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.


(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

[Continued on next page]

(54) Title: PLASMA ASSISTED REACTOR



(57) Abstract: A plasma assisted reactor for the removal of carbonaceous combustion products or for simultaneous removal of carbonaceous combustion products and nitrogen oxides from the exhaust emissions from an internal combustion engine, wherein the reactor includes a gas permeable bed made at least primarily of an active material having the general formula $A_{1-x}A'_xB_{1-y}B'_yO_3$ or $M_xM'_{1-x}VO_3$ or $M_4V_2O_7$.



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

- 1 -

Plasma Assisted Reactor

The present invention relates to the plasma-assisted processing of gaseous media and in particular to the
5 reduction of the emission of particulate including carbonaceous particulate, and/or nitrogen oxides, hydrocarbons including polyaromatic hydrocarbons, carbon monoxide and other regulated or unregulated combustion products from the exhausts of internal combustion
10 engines.

One of the major problems associated with the development and use of internal combustion engines is the noxious exhaust emissions from such engines. Two of the
15 most deleterious materials, particularly in the case of diesel engines, are particulate matter (including carbonaceous particulate) and oxides of nitrogen (NO_x). Increasingly severe emission control regulations are forcing internal combustion engine and vehicle
20 manufacturers to find more efficient ways of removing these materials in particular from internal combustion engine exhaust emissions. Unfortunately, in practice, it is found that techniques which improve the situation in relation to one of the above components of internal
25 combustion engine exhaust emissions tend to worsen the situation in relation to the other. A variety of systems for trapping particulate emissions from internal combustion engine exhausts have been investigated, particularly in relation to making such particulate
30 emission traps capable of being regenerated upon accumulation therein of particulate material.

Examples of such diesel exhaust particulate filters are to be found in European patent application EP 0 010

- 2 -

384; US patents 4,505,107; 4,485,622; 4,427,418; and
4,276,066; EP 0 244 061; EP 0 112 634 and EP 0 132 166.

5 In all the above cases, the particulate matter is
removed from diesel exhaust gases by a simple physical
trapping of particulate matter in the interstices of a
porous, usually ceramic, filter body, which is then
regenerated by heating the filter body to a temperature
10 at which the trapped diesel exhaust particulates are
burnt off. In most cases the filter body is monolithic,
although EP 0 010 384 does mention the use of ceramic
beads, wire meshes or metal screens as well. US patent
4,427,418 discloses the use of ceramic coated wire or
ceramic fibres.

15

In a broader context, the precipitation of charged
particulate matter by electrostatic forces also is known.
However, in this case, precipitation usually takes place
upon larger planar electrodes or metal screens.

20

GB patent 2,274,412 discloses a method and apparatus
for removing particulate and other pollutants from
internal combustion engine exhaust gases, in which the
exhaust gases are passed through a bed of charged pellets
25 of material, preferably ferroelectric, having high
dielectric constant. In addition to removing
particulates by oxidation, especially electric discharge
assisted oxidation, there is disclosed the reduction of
NO_x gases to nitrogen, by the use of pellets adapted to
30 catalyse the NO_x reduction.

Also, US patents 3 983 021, 5 147 516 and 5 284 556
disclose the catalytic reduction of nitrogen oxides.
However, US 3 983 021 is solely concerned with the
35 reduction of NO to N in a silent glow discharge, the

- 3 -

temperature of which is kept below a value at which the oxidation of N or NO to higher oxides of nitrogen does not occur.

5 Although, so-called contact bodies are used in the process of US 3 983 021, and some of those disclosed may have some catalytic properties, catalysis does not appear to be a necessary feature of the process of US 3 983 021. Other surface properties, such as adsorption on large
10 surface area materials, are the basis of the process of US 3 983 021.

US patent 5 147 516 does refer to the use of catalysts to remove NO_x, but the catalytic materials
15 involved are defined very specifically as being sulphur tolerant and deriving their catalytic activity from their form rather than their surface properties. The operating conditions are very tightly defined. There is no specific mention of the type, if any, of electric
20 discharge involved. All that is disclosed is that the NO_x removal depends upon electron-molecule interactions, facilitated by the structure of the 'corona-catalytic' materials not the inter-molecular interactions involved in the present invention.

25

US patent 5 284 556 does disclose the removal of hydrocarbons from internal combustion engine exhaust emissions. However, the process involved is purely one of dissociation in an electrical discharge of the so-called 'silent' type, that is to say, a discharge which
30 occurs between two electrodes at least one of which is insulated. The device described is an open discharge chamber, not a packed bed device. Mention is made of the possible deposition of a NO_x-reducing catalyst on one of
35 the electrodes.

The specification of application WO 00/71866 describes the use of a dielectric barrier reactor for the processing of exhaust gases from internal combustion engines to remove nitrogenous oxides, particulate including carbonaceous particulate, hydrocarbons including polyaromatic hydrocarbons, carbon monoxide and other regulated or unregulated combustion products. A feature of this reactor is that the flow of the gaseous medium between entering and leaving the reactor has axial, radial and circumferential components. Reference is made to a gas permeable bed of a dielectric medium contained in the space between the electrodes and adapted to have catalytic properties to increase the efficiency of oxidation of particulates and/or reduction of nitrogen oxides.

In accordance with the invention the efficiency of oxidation of particulates and reduction of nitrogen oxides is improved by using a combination of catalyst materials and plasma discharge. Examples of these materials are metavanadates, pyrovanadates and perovskites. Metavanadate materials have the general formula MVO_3 where M is a cation for example an alkali metal cation while metal-substituted metavanadates have the general formula $M_{1-x}M^1_xVO_3$ where M is a cation for example an alkali metal cation and M^1 is a cation for example Cu. Examples of metavanadate (MVO_3) materials are KVO_3 , $CsVO_3$, $RbVO_3$ and $CuVO_3$ and metal-substituted alkali-metal vanadates such as $K_{0.7}Cu_{0.3}VO_3$. Pyrovanadate materials have the general formula $M_4V_2O_7$ and $M_{4-4x}M^1_{4x}V_2O_7$ where M and M^1 are cations. Examples of pyrovanadates ($M_4V_2O_7$) are $Cs_4V_2O_7$, $Rb_4V_2O_7$ and $K_4V_2O_7$.

- 5 -

The use of potassium and caesium vanadate and pyrovanadate materials for the low temperature combustion of carbon in simulated diesel emissions, down to as low as 225°C for $\text{Cs}_4\text{V}_2\text{O}_7$ has been discussed by G Saracco et al in a paper 'Development of Catalysts Based on Pyrovanadates for Diesel Soot Combustion' in Applied Catalysis B: Environmental, volume 21, 233-242, 1999. Here dry soot almost free of any adsorbed hydrocarbons was generated from an ethyne burner.

The use of copper vanadates CuVO_3 , $\text{Cu}_3(\text{VO}_4)_3$ and copper-substituted potassium vanadate $\text{K}_{0.7}\text{Cu}_{0.3}\text{VO}_3$ as carbon combustion catalysts in the absence and presence of metal chloride salts such as potassium chloride in which an amorphous carbon black powder was a simulant for diesel emissions have also been discussed by V Serra et al in a paper 'Combustion of carbonaceous materials by Cu-K-V based catalysts. II. Reaction mechanism' in Applied Catalysis B: Environmental, volume 11, 329-346, 1997. Carbon combustion temperatures as low as 382°C compared with non-catalytic combustion temperatures of 616°C were observed.

The materials under investigation in the above two papers were heated but not subjected to external influences such as electric fields in particular those associated with non-thermal plasmas and the design of practical reactors incorporating these materials for use in internal combustion engines was not considered.

Perovskites have the general formula ABO_3 where A and B are cations and A is the cation with the larger radius. There are many perovskite materials for example LaMnO_3 ,

- LaAlO₃, SrZrO₃, BaCeO₃ as discussed by T Shimuzu in a paper 'Partial Oxidation of Hydrocarbons and Oxygenates Compounds on Perovskite Oxides' in Catal. Rev-Sci. Eng., volume 34, 355-371, 1992 while other examples include
- 5 LaNiO₃, LaFeO₃, LaCrO₃, LaCoO₃, LaMnO₃, BaCrO₃, BaCoO₃, BaFeO₃, BaNiO₃, PbTiO₃. Substitution by other metal cations of the A and or B sites yields perovskites with the general composition $A_{1-x}A^1_xB_{1-y}B^1_yO_3$ examples of which are Ba_{0.8}Sr_{0.2}NiO₃, Ba_{0.8}Sr_{0.2}CrO₃, La_{0.8}Sr_{0.2}NiO₃,
- 10 La_{0.9}K_{0.1}CoO₃, La_{0.9}K_{0.1}FeO₃ and La_{0.6}Cs_{0.4}CoO₃. The latter composition has been described by Yang et al in a paper 'Simultaneous catalytic removal of NO and carbon particulates over perovskite-type oxides, in Journal of Industrial and Engineering Chemistry, volume 4, 263-269,
- 15 December 1998. Another perovskite composition is La_{0.8}Sr_{0.2}Mn_{0.5}Cu_{0.5}O₃ as described by Duriez et al in the paper 'Simultaneous NO_x reduction and soot elimination from diesel exhausts on perovskite-type oxide catalysts' in Catalysts and Automotive Pollution Control III,
- 20 Elsevier, 1995, edited by A Frennet and J-M Bastin, pages 137-147. In a general sense A and A¹ can include La, Sr, K, Na, Li, Cs, Pb and Ba while B and B¹ can include Ni, Cr, Co, Mn, Ti, Zr, Ce, Cu and V. Layered perovskite materials have the general formula $A_{2-x}A^1_xB_{1-y}B^1_yO_4$ or when
- 25 $A = A^1$ and $B = B^1$, A₂BO₄ and examples are described in a paper by Y Teraoka et al in a paper 'Simultaneous Catalytic Removal of NO_x by Diesel Soot and NO_x by Perovskite-Related Oxides', in Catalysis Today, volume 27, 107-115, 1996 and in WO99/38603. Perovskite
- 30 compositions are also described by VI Parvulescu et al in a paper 'Catalytic removal of NO' in Catalysis Today,

- 7 -

volume 46, 233-316, 1998.

Perovskite materials of the form ABO_3 have been evaluated for the simultaneous removal of nitrogenous
5 oxides and diesel soot particulates obtained by the incomplete combustion of diesel fuel as described by Y Teraoka et al in a paper 'Simultaneous Removal of Nitrogen Oxides and Diesel Soot Particulates Catalysed by Perovskite-Type Oxides' in Applied Catalysis B:
10 Environmental, volume 5, L181-1185, 1995.

Perovskite materials of the form ABO_3 have also been used for the conversion of oxidative and reductive gases, in exhaust gases to harmless gases as described in EP
15 0089199 A2 ('Catalysts for Converting Reductive and Oxidative Gases of Exhaust Gases into Innoxious Gases').

Perovskites were of the form $La_{(1-x)/2}Sr_{(1+x)/2}CO_{1-x}Me_xO_3$ in which Me is an element selected from the group consisting of Fe, Mn, Cr, V and Ti and x is a number
20 between 0.15 and 0.90. Conversion of CO was carried out in a lean atmosphere containing oxygen while conversion of a mixture of CO, NO_2 and gaseous hydrocarbon or a mixture of CO and NO_2 was successfully achieved by the perovskite material at for example 300°C for the
25 conversion of CO alone. EP 0089199 does not describe the use of perovskite materials for conversion of diesel soot particulates in an exhaust gas.

Perovskite materials under investigation in the
30 above examples were heated but not subjected to external influences such as electric fields in particular those associated with non-thermal plasmas and the design of practical reactors incorporating these materials for use in internal combustion engines was not considered by

- 8 -

these authors.

According to the present invention there is provided a reactor for the plasma assisted processing of internal combustion engine exhaust gases to reduce the emissions of unwanted carbonaceous combustion products or for simultaneous removal of unwanted carbonaceous combustion products and nitrogen oxides, the reactor including a reactor chamber adapted to be connected into the exhaust system of an internal combustion engine and including at least one gas permeable body of active material adapted in the presence of a gaseous discharge in the exhaust gases for the oxidation of carbonaceous combustion products or for simultaneous oxidation of carbonaceous combustion products and catalytic reduction of nitrogen oxides present in the exhaust gases, means for exciting a non-thermal plasma in the exhaust gases and means for constraining the excited exhaust gases to flow through the body of active material, wherein the active material comprises at least primarily perovskites or vanadates selected from a group comprising perovskite materials having the general formula $A_{1-x}A^1_xB_{1-y}B^1_yO_3$, vanadate materials having the general formula $M_4V_2O_7$ or MVO_3 or $M_{44x}M^1_{4x}V_2O_7$ or $M_{1-x}M^1_xVO_3$ and combinations thereof.

25

The arrangement within the reactor chamber may be such that the plasma may be generated in the exhaust gases within the interstices of the body of active material, or if more than one body of active material is used, within the interstices of one of the bodies of active material.

Alternatively the exhaust gases can be excited into the plasma state prior to their passage through the said body of active material.

- 9 -

Suitable elements for the components A,A¹ include but are not restricted to La, Sr, K, Na, Li, Cs, Pb and Ba and suitable elements for the components B,B¹ of the perovskite active materials include but are not
5 restricted to Ni, Cr, Co, Fe, Mn, Ti, Zr, Ce, Cu and V.

Examples of pyrovanadates (M₄V₂O₇) are Cs₄V₂O₇, Rb₄V₂O₇ and K₄V₂O₇.

10

Examples of metavanadate (MVO₃) materials are KVO₃, CsVO₃, RbVO₃ and CuVO₃ and metal-substituted alkali-metal vanadates such as K_{0.7}Cu_{0.3}VO₃.

15

The reactor may have a single reactor chamber in which are situated both the means for exciting the exhaust gases into the plasma state and the gas permeable body of active material. Alternatively, the reactor chamber may be divided into two regions in one of which
20 the exhaust gases are excited into the plasma state and in the other of which the excited exhaust gases are contacted with the active material. Alternatively exhaust gases can be contacted with the active materials before they are excited into the plasma state.

25

Also according to the present invention there is provided a method of treating exhaust gases from an internal combustion engine to reduce the emissions of unwanted carbonaceous combustion products and nitrogen
30 oxides therefrom including the operations of exciting the exhaust gases into a plasma state and passing the excited exhaust gases through a gas permeable body of active material consisting at least primarily of perovskite

- 10 -

materials having the general formula $A_{1-x}A_x^1B_{1-y}B_y^1O_3$,
vanadate materials having the general formula $M_4V_2O_7$ or
 $M_xM_{1-x}^1VO_3$ or combinations or mixtures thereof.

5 The exhaust gases may be excited into a plasma state
prior to their passage through the gas permeable body of
perovskite or vanadate materials, or within the
interstices of the gas permeable body of perovskite or
vanadate containing material.

10 The gas permeable body of perovskite or vanadate-
containing material may include other materials such as
zeolites which are active for the reduction of nitrogen
oxides contained in the exhaust gases as described in WO
15 99/12638.

 The plasma region of the reactor may be a pellet bed
reactor such as is described in GB 2,274,412, a corona
discharge reactor such as a pulsed corona or continuous
20 wave corona reactor examples of which are described in
our specifications GB 2282738 B and WO99/15267, a
dielectric barrier reactor, a surface barrier reactor as
described in specification WO 00/43102 or any other non-
thermal or thermal reactor for the plasma assisted
25 treatment of the exhaust gases from internal combustion
engines to remove noxious combustion products therefrom.
The plasma generating region may include additional
catalytic components besides the active material
described here or be installed as part of an emissions
30 control system employing catalysts or other emission
control devices.

 The gas permeable bed of active material, perovskite
or vanadate can be in the form of spheres, pellets,
35 extrudates, fibres, sheets, wafers, frits, meshes, coils,

- 11 -

foams, membrane, ceramic honeycomb monolith or granules or as a coating or contained within a dielectric, polymeric or metallic material in any of the above shapes. For slightly soluble materials such as
5 vanadates, containment in the pores of a ceramic foam can be used. The materials of the present invention can also act as selective filters as described in the specification of applications GB 99 24999.7, GB 99 29771.5 and GB 00 08351.9. respectively.

10

Utilising the combination of components, plasma together with perovskite or vanadate or mixtures thereof offers advantages over the employment of one component alone.

15

Thus a material which is not significantly catalytic at a low temperature for the oxidation of carbonaceous particulate or reduction of nitrogenous oxides by thermal mechanisms, may develop or exhibit enhanced catalytic
20 properties for these processes when exposed to a plasma. This may be due, for example to activation by O atoms or other plasma generated species such as O_2^+ molecular ions or OH radicals or nitrogen dioxide. Catalytic or non-catalytic material properties can be further augmented by
25 the electric field or other charged species present in or adjacent to the plasma region.

In addition the combination of plasma and catalyst offers synergies for the combined system being more
30 efficient than either mode of operation alone for removal of unwanted emissions from internal combustion engine

- 12 -

exhaust. The combined plasma/catalyst system may for example operate over a wider temperature range than thermal catalysts only. Further the presence of catalyst within the plasma or in combination with a plasma reactor, which may be packed or unpacked, provides for a reduction in the electrical power requirement of the plasma reactor at temperatures at which the catalyst is naturally active. This is because, at such temperatures, the catalyst is efficient enough without additional plasma enhancement.

When the exhaust gases contain nitrogenous oxides and carbonaceous combustion products such as carbonaceous particulates that are derived from an internal combustion engine supplied with combustion fuel, the exhaust gases can contain hydrocarbon, either added separately or residually derived from the fuel combustion. The exhaust gases also can contain a chemical additive acting as a carbon combustion catalyst that is either present initially in the fuel or added separately to the exhaust gases and whose function is to lower the combustion temperature and/or increase the rate of removal of carbonaceous material. Carbon combustion catalyst to be added to the fuel can be encapsulated within or bound to a fugitive additive that chemically decomposes during or shortly after fuel combustion thus releasing the additive into the fuel or exhaust. Examples of carbon combustion catalysts are alkali-metal salts such as lithium nitrate described in GB 2 232 613 B, cerium oxide, alkali-metal doped lanthanum oxide-vanadium oxide in addition to the active materials, perovskites and vanadates described here. The mode of operation of such catalysts is described in WO 00/43102.

- 13 -

The invention will now be described, by way of example, with reference to the accompanying drawings in which,

5 Figure 1 is a longitudinal section of a reactor embodying the invention for the removal of carbonaceous combustion products or for simultaneous removal of carbonaceous combustion products and nitrogen oxides from the exhaust emissions from an internal combustion engine,

10

Figure 2 is a longitudinal section of a second embodiment of the invention,

Figure 3 is a longitudinal section of a third
15 embodiment of the invention for the removal of carbonaceous combustion products or for simultaneous removal of carbonaceous combustion products and nitrogen oxides from the exhaust emissions from an internal combustion engine and

20

Figure 4 is a schematic view showing the gas path through the embodiment shown in Figure 3. Both Figure 3 and Figure 4 are described in application WO 00/71866.

25 Referring to Figure 1 of the drawings, a reactor for removing carbonaceous combustion products, or for simultaneous removal of carbonaceous combustion products and nitrogen oxides from the exhaust gases from an internal combustion engine consists of a cylindrical
30 stainless steel chamber 2 which has an inlet stub 3 and an outlet stub 4 by means of which it can be connected into the exhaust system of an internal combustion engine. The chamber 2 is arranged, in use, to be connected to an earthing point 5. Perforated cylindrical stainless steel
35 inner and outer electrodes 6 and 14 are positioned co-axially within the chamber 2 by means of two electrically

- 14 -

insulating supports 7 and 8. The insulating support material can be made of a ceramic material such as alumina or MICATHERM (Registered Trade Mark) as described in WO99/20373. The space 11 bounded by the electrodes 6 and 14 and the supports 7 and 8 is filled, in this example, with a bed of gas permeable active material for example vanadate or perovskite or mixtures of these materials illustrated highly diagrammatically at 12.

10 The bed of gas permeable active material, perovskite or vanadate can be in the form of spheres, pellets, extrudates, fibres, sheets, wafers, frits, meshes, coils, foams, membrane, ceramic honeycomb monolith or granules or as a coating, on or contained within a dielectric material in any of the plasma shapes. For slightly active soluble material such as vanadates containment in the pores of a ceramic foam can be used. Examples of such foams are, but not exclusively, alumina foams produced by Porvair Advanced Materials, Hendersonville, North Carolina, USA. The upstream end of the inner electrode 6 is arranged to be connected via an insulating feedthrough 10 to a source 9 of an electrical potential sufficient to excite a plasma in the exhaust gases in the interstices between the active material 12. The plasma generating means 9 is not shown in detail because it can take a number of forms.

A convenient potential for the excitation of the plasma is of the order of kilovolts to tens of kilovolts and repetition frequencies in the range 50 to 5000 Hz, although higher frequencies of the order of tens of kilohertz can be used. Pulsed direct current is convenient for automotive use, but alternating potentials for example triangular or sine waves of the same or similar characteristics can be used.

- 15 -

The support 7 near the inlet stub 3 has a number of axial holes 13 disposed regularly around its periphery so that incoming exhaust gases are constrained to pass into the space 15 between the outer electrode 14 and the chamber 2 of the reactor 1 and thence radially through the bed 12 of active material before passing through the inner electrode 6 and leaving the chamber 2 via the exhaust stub 4.

Examples of vanadates such as metavanadate and pyrovanadate compositions that can be used in the bed of active material are KVO_3 , CsVO_3 , RbVO_3 , $\text{K}_4\text{V}_2\text{O}_7$, $\text{Cs}_4\text{V}_2\text{O}_7$, $\text{Rb}_4\text{V}_2\text{O}_7$. Metal-substituted alkali-metal vanadates for example $\text{K}_{0.7}\text{Cu}_{0.3}\text{VO}_3$ are also useful materials for the removal of carbonaceous material, while examples of perovskites which are useful materials for the simultaneous removal of carbonaceous materials and nitrogen oxides are $\text{Ba}_{0.8}\text{Sr}_{0.2}\text{NiO}_3$, $\text{Ba}_{0.8}\text{Sr}_{0.2}\text{CrO}_3$, $\text{La}_{0.8}\text{Sr}_{0.2}\text{NiO}_3$, $\text{La}_{0.9}\text{K}_{0.1}\text{CoO}_3$, $\text{La}_{0.9}\text{K}_{0.1}\text{FeO}_3$, $\text{La}_{0.6}\text{Cs}_{0.4}\text{CoO}_3$ and $\text{La}_{0.8}\text{Sr}_{0.2}\text{Mn}_{0.5}\text{Cu}_{0.5}\text{O}_3$.

Other embodiments are known in which the reactor can be separated into chambers so that the gaseous medium can be contacted with an active material before entering the plasma region of the reactor, or can be excited in the plasma region and then be contacted with the active material housed in the plasma region, or can be excited in the plasma region and then passed through the active material that is housed outside of the plasma region of the reactor. As an example of this Figure 2 shows a second embodiment of the invention in which those components which are similar to corresponding components of the first embodiment have the same reference numerals. The reactor chamber 1 is extended and contains a first

- 16 -

plasma excitation reactor similar to that described above with reference to Figure 1, and a second reactor chamber similar in layout to the first reactor but in which there are no electrical connections to the bed of active material 11 of vanadate or perovskite material, so that exhaust gases can be excited into a plasma state in the first chamber before contacting the active material. The arrangement can be reversed so that the exhaust gases can be contacted with an active material which does not require the exhaust gases to be excited, before being contacted in an excited state with the active materials of the present invention. Also a chamber can be left empty of active material when in use. Other arrangements of chambers are described in Figure 8 of publication WO99/12638 and arrangements that use axial flow through the permeable bed of material can also be used. An arrangement involving an unpacked plasma region followed by catalyst can also be used.

Referring to Figure 3, a second reactor for the plasma assisted processing of the exhaust emissions from internal combustion engines to remove noxious components therefrom consists of a reactor chamber 31 which has inlet and outlet stubs 32,33, respectively, by means of which it can be incorporated into the exhaust system of an internal combustion engine, as before.

Inside the reactor chamber 31 there is an inner electrode 34 which is supported within a dielectric tube 35, made for example out of α -alumina which has its upstream end closed by a spherical dome 36 to facilitate the flow of exhaust gases through the reactor. The inner surface of the dielectric tube can be metallised with a

- 17 -

metal coating in order to increase the physical contact between the electrode and dielectric tube although in this example, the inner electrode 34 is conveniently provided by a deposited electrically conducting layer of silver on the inner surface of the dielectric tube 35. High voltage connection via the high voltage input terminal 37 is made through a spring loaded telescopic tube assembly 38 and spring contacts 39. Load from the sprung telescopic tube assembly 38 is received by a load spreader plate 310, which is connected to the conducting layer of silver forming the inner electrode 34. The materials, including the spring are required to operate at elevated temperatures, and the spring must have low creep at such temperatures. A preferred material for the spring is an Inconel alloy such as X750. Alumina end flange 311 is shaped to receive and locate the end of the dielectric tube 35 and is itself located by a sprung metal clip 312.

A potential of the order of kilovolts to tens of kilovolts and repetition frequencies in the range 50 to 5000 Hz can be applied to the inner electrode 34 through the high voltage input terminal 37. Concentric with the inner electrode 34 and dielectric tube 35 is a grounded outer electrode 313 made for example of stainless steel. At the inlet end of the reactor the spherical dome of the dielectric tube 35 is in contact with a compliant heat resistant material 314 that rests in the curved part of the outer electrode 313 and held in place by a metallic ring 315 with a series of screws.

- 18 -

As shown in Figure 4, the outer electrode 413 has a series of baffles 416 and slots 417, 417a. The baffles 416 extend from the outer electrode 413 to the inner surface of the wall of the reactor chamber 41 and act as grounding connections as well as causing the exhaust gases to follow a convoluted path which has both axial, and circumferential components and being at least partially helical. There is also a radial component of flow, initially inwardly as the gas transfers from outside the outer electrode 413 to the space between the electrode 413 and dielectric tube 43 which corresponds to dielectric tube 35 in Figure 3, and then outwardly as the gas returns to exit from outside the outer electrode 413. Thus there is also a spiral component in the flow.

The baffle 416 is arranged to divide the space between the electrode 413 and the reactor chamber 41 into six segments. At the gas inlet end three of these segments are closed off at 416a, 416b and 416c to axial gas flow and the remaining three segments are open to axial gas flow into the space between the electrode 413 and the reactor chamber 41. These latter three segments are closed off by the baffle 416 at the gas outlet end of the reactor. Consequently the gas is forced to pass via slot 417 radially into the space between the electrodes 413 and 43 then passing in at least a partially helical manner before passing radially via the next slot 417a into the next segment of space between electrode 413 and reactor chamber 41. The baffle 416 leaves open this

- 19 -

segment at the gas outlet end, allowing exhaust of the treated gas to exit the reactor. Thus it will be seen that the exhaust gases both enter and leave the main part of the reactor 41 along the surface of the outer
5 electrode 413. Thus for a given gas velocity, the residence time of the exhaust gases in the electric field is increased compared with either purely axial or radial flow. Note that in Figure 4 part of the electrode 413 has been shown cut away at 418. This cut away is shown in the
10 Figure only to illustrate the flow of the exhaust gases as they pass between the electrodes and does not represent a structural feature of the reactor.

The embodiments of reactor described in these
15 examples may include further catalytic components, or be installed as part of an emissions control system employing catalysts or other emission control devices for the plasma assisted treatment of the exhaust gases from internal combustion engines. Such other emission control
20 devices may comprise exhaust gas recirculation (EGR), variations in ignition timing, fuel injection timing and fuel injection pulse rate shaping. The plasma generation means is not shown in detail but an example is shown in WO 00/50746. An article 'Stop go systems get the green
25 light' in European Automotive Design, April 1998, pages 24-26 describes an example of an integrated starter alternator damper system (ISAD). Such an ISAD can be used as part of a power supply system to power a plasma assisted emissions control system of which a reactor as
30 described herein is part. In addition, other power sources such as but not limited to single/multiple output alternator technologies e.g. 14 V or 14V/42V, fuel cells, gas turbines, solar cells and heat exchangers can be the

- 20 -

primary or part-provider of the electrical-generating power source that can also be used to power the power supply system for the reactor.

5 Zeolite materials, aluminas, metal-doped aluminas and metal oxide containing aluminas are particularly useful for the treatment of nitrogenous oxides and can be used in conjunction with vanadate and perovskite materials or with mixtures of these to increase reduction
10 of nitrogenous oxides to nitrogen. Examples of zeolites are those known as ZSM-5, Y, beta, mordenite all of which may contain iron, cobalt or copper with or without additional catalyst promoting cations such as cerium and lanthanum. Other examples of zeolites are alkali metal
15 containing zeolites, in particular sodium-Y zeolites that are particularly useful for treatment of nitrogenous oxides. Ferrierites, in particular silver containing ferrierite with silver contents up to 10 weight percent, are also particularly useful zeolite materials for the
20 removal of nitrogen oxides. The zeolite material and aluminas can be in the form of spheres, pellets, extrudates, fibres, sheets, wafers, frits, meshes, coils, foams, membrane, ceramic honeycomb monolith or granules or as a coating on or contained within a dielectric,
25 polymeric or metallic material in any of the above shapes.

Exhaust gases containing hydrocarbon reductant residually-derived from the fuel combustion, or added
30 separately, or including a nitrogen-containing reductant for the reduction of nitrogenous oxides and/or including a carbon combustion catalyst, as described earlier, can be passed through the plasma region of the plasma reactor which contains materials active for the removal of
35 carbonaceous material or nitrogen oxides or both, or can be passed through a bed of such materials before entering

- 21 -

the plasma region, or can be passed over one or more of these materials after passing through the plasma region. When a nitrogen-containing reductant is used, the reductant can be added to the exhaust gases leaving the
5 plasma region of the reactor and before their passage through the catalytically second chamber of the reactor.

Claims

1. A reactor for the plasma assisted processing of internal combustion engine exhaust gases to reduce the emission of unwanted carbonaceous combustion products and nitrogen oxides therefrom, the reactor including a reactor chamber adapted to be connected into the exhaust system of an internal combustion engine and including at least one gas permeable body of active material adapted in the presence of a gaseous discharge in the exhaust gases for the oxidation of carbonaceous combustion products or for the simultaneous oxidation of carbonaceous combustion products and catalytic reduction of nitrogen oxides present in the exhaust gases, means for exciting a non-thermal plasma in the exhaust gases and means for constraining the excited exhaust gases to flow through the body of active material, wherein the active material comprises at least primarily a perovskite or vanadate including metavanadate and pyrovanadate selected from a group comprising perovskite materials having the general formula $A_{1-x}A^1_xB_{1-y}B^1_yO_3$, vanadate materials having the general formula $M_4V_2O_7$ or $M_{1-x}M_xVO_3$ and combinations thereof.
2. A reactor according to claim 1 wherein the components A, A^1 of the perovskite materials are selected from the group comprising La, Sr, K, Li, Na, Cs, Pb and Ba.
3. A reactor according to claim 1 or claim 2 wherein the components B, B^1 of the perovskite material are selected from the group comprising Ni, Cr, Co, Mn, Ti, Zr, Cu and V.

- 23 -

4. A reactor according to any of claims 1 to 3 wherein the component M of the vanadate material having the general formula $M_4V_2O_7$ is K, Cs or Rb.
- 5 5. A reactor according to any of claims 1 to 4 wherein the components M, M^1 of the vanadate material having the general formula $M_xM_{1-x}^1VO_3$ are the same.
6. A reactor according to any of claims 1 to 3 wherein
10 the components M, M^1 of the vanadate material having the general formula $M_{1-x}M_x^1VO_3$ are alkali metals.
7. A reactor according to claim 6 wherein the
15 components M, M^1 of the vanadate material are K and Cu respectively.
8. A reactor according to claim 7 wherein the vanadate material has the formula $K_{0.7}Cu_{0.3}VO_3$.
- 20 9. A reactor according to any preceding claim wherein the gas permeable bed of active material is contained between gas permeable electrodes by means of which there can be applied across the bed of active material a potential difference sufficient to excite the exhaust
25 gases into the plasma state in the interstices of the gas permeable body of active material.
10. A reactor according to any of claims 1 to 8 wherein there is included means for exciting the exhaust gases
30 into the plasma state prior to its passage through the bed of active material.
11. A reactor according to claim 10 wherein the means

- 24 -

- for exciting the exhaust gases into the plasma state includes a gas permeable body of dielectric material contained between gas permeable electrodes by means of which there can be applied across the gas permeable body of dielectric material a potential sufficient to excite the exhaust gases into the plasma state in the interstices of the gas permeable body of dielectric material.
- 10 12. A reactor according to claim 11 wherein the dielectric material is adapted to participate in the oxidation of carbonaceous combustion products or the simultaneous removal of carbonaceous combustion products and nitrogen oxides present in the exhaust gases.
- 15 13. A reactor according to any preceding claim wherein the gas permeable body of carbon combustion active material also includes a zeolite material for the reduction of nitrogen oxides.
- 20 14. A reactor according to claim 13 wherein the zeolite material includes at least one type selected from the group including the zeolite known as ZSM-5, Y, beta, mordenite, ferrierite and alkali metal-containing zeolites.
- 25 15. A reactor according to claim 14 wherein the zeolite materials contain iron, cobalt or copper.
- 30 16. A reactor according to claim 14 or claim 15 wherein the zeolite material includes a catalysis-promoting cationic species.
- 35 17. A reactor according to claim 16 wherein the catalysis promoting cationic species is cerium or lanthanum.

- 25 -

18. A reactor according to claim 14 wherein the zeolite material is a sodium-Y zeolite.

5 19. A reactor according to claim 13 wherein the zeolite material is a silver containing ferrierite.

20. A reactor according to claim 19 wherein the ferrierite contains up to ten weight per cent of silver.

10

21. A method of treating the exhaust gases from an internal combustion engine to reduce the emission of unwanted carbonaceous combustion products or the simultaneous removal of unwanted carbonaceous combustion products and nitrogen oxides therefrom, including the operations of exciting the exhaust gases into a plasma state and passing the exhaust gases through a gas permeable body of active material consisting at least primarily of perovskite materials having the general formula $A_{1-x}A_x^1B_{1-y}B_y^1O_3$, or vanadate materials having the general formula $M_xV_2O_7$, or $M_xM_{1-x}^1VO_3$, or combinations thereof.

22. A method according to claim 21 wherein the exhaust gases are excited into a plasma state prior to their passage through the said gas permeable body of active material.

23. A method according to claim 21 wherein there is included the operation of contacting the exhaust gases with a material active to promote the reduction of nitrogen oxides present in the said exhaust gases.

24. A method according to claim 22 wherein the material active to promote the reduction of nitrogen oxides

- 26 -

present in the exhaust gases is a zeolite material.

25. A method according to claim 23 wherein the zeolite material is included in the said body primarily of active
5 perovskite or vanadate material.

26. A method according to any of claims 21 to 24 wherein the exhaust gases are excited into the plasma state prior to their passage through the body primarily of perovskite
10 or vanadate material.

27. A method according to any of claims 21 to 25 wherein a hydrocarbon reductant material is included in the exhaust gases prior to their excitation into the plasma
15 state, the hydrocarbon reductant material being adapted to produce under the influence of the plasma species which enhance the reduction of nitrogen oxides contained in the exhaust gases.

20 28. A reactor for the removal of at least carbonaceous combustion products from the exhaust gases of internal combustion engines substantially as hereinbefore described and with reference to the accompanying drawings.

25 29. A method of removing at least carbonaceous combustion products from the exhaust gases from internal combustion engines substantially as hereinbefore described.

Fig. 1.




Fig.2.




Fig.3.





Fig.4.



INTERNATIONAL SEARCH REPORT

Int. lation Application No

PCT/GB 01/00442

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 F01N3/01 F01N3/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 F01N B01J B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 99 38603 A (AEA TECHNOLOGY PLC ;SEGAL DAVID LESLIE (GB)) 5 August 1999 (1999-08-05) page 6, line 24 -page 9, line 24 figures	1-3, 9-12, 21-23, 26,28,29
Y	US 4 485 191 A (SEKIDO SATOSHI ET AL) 27 November 1984 (1984-11-27) column 3, line 12 -column 4, line 40 figure 9 --- -/--	1-3, 9-12, 21-23, 26,28,29

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

18 July 2001

Date of mailing of the international search report

25/07/2001

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax (+31-70) 340-3016

Authorized officer

Ingegneri, M

INTERNATIONAL SEARCH REPORT

Int lional Application No

PCT/GB 01/00442

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>WO 98 32531 A (UNIV OKLAHOMA STATE) 30 July 1998 (1998-07-30)</p> <p>page 18, line 1 - line 19 figure 1</p> <p>-----</p>	<p>1-3, 9, 13, 14, 16, 18, 21, 24, 25, 28, 29</p>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 01/00442

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9938603 A	05-08-1999	AU 2177399 A EP 1051234 A	16-08-1999 15-11-2000
US 4485191 A	27-11-1984	JP 58156350 A DE 3379215 D EP 0089199 A	17-09-1983 30-03-1989 21-09-1983
WO 9832531 A	30-07-1998	AU 6242398 A US 6159432 A	18-08-1998 12-12-2000

Form PCT/ISA/210 (patent family annex) (July 1992)